





Hamilton Taping





Hamilton Drywall Products Taping Compound is a light-weight pre-mixed, high performance, drywall joint compound. It is recommended for embedding tape and paper trim to gypsum drywall installations. It has excellent bond, workability, slip, open-time and working time. Meets ASTM Standard C475.

Standards:	Taping meets or exceeds ASTM C-475 "Standard specification for Joint Compound and Joint Tape for Finishing Gypsum Board".
Job Conditions:	Maintain a minimum air, surface and compound temperature of 10° C (50° F) for 48 hours prior to application and until dry and stable.
Surface Preparation:	All surfaces must be firm, clean, dry and free of foreign substances. Open spaces between panels of 3mm (1/8") or more should be pre-filled with compound at least 24 hours prior to embedding or first coat work. Hamilton Drywall Products Ultra-Fill or Smooth Set Lites are recommended for larger fills.
Mixing:	In a clean container mix mechanically to a smooth, creamy consistency, adding water as required. Add water in 125 ml (1/2 cup) increments to avoid over thinning.
Application:	For interior use only. Apply with hand or mechanical tools. Fill joint with a thin layer of compound, embed tape - leaving about 0.8 -1 mm (1/32") of compound under the tape – wipe lightly to remove excess compound and let dry. Allow compound to dry thoroughly before filling and finishing.
Coverage/Yield:	17 litre carton — Approximate coverage - 130-150 square meters (1400-1614 square feet). Approximate yield - 17-23 litres depending on application. 18 litre pail — Approximate coverage - 150-174 square meters (1614-1872 square feet). Approximate yield - 18-24 litres depending on application.
Storage/Shelf Life:	Rotate inventory within 90 days of the production date on the package. Store in a dry environment, away from freezing, extreme heat and direct sunlight. For best results use within 6 months.

	Submittal Approvals
Job Name:	
Contractor:	Date: