



Hamilton Ultra-Ceil



Hamilton Drywall Products Ultra-Ceil is a light weight, gypsum plaster based compound used for smoothing and finishing interior concrete ceilings. It is not corrosive, mixes very easily without lumps and has excellent workability. It has good coverage and adheres well to properly prepared concrete ceilings.

Set Time: _____

Ultra-Ceil has an approximate working time of 2.5 hours.
Factors That Can Affect Set Time: Thickness of mixed material, mixing time, temperature (air and/or water), remixing or re-tempering, hardness of water, dirty tools, intermixing of materials, humidity and previously mixed or set Ultra-Ceil.

Job Conditions: _____

Maintain a minimum air, surface and material temperature of 10° C (50° F) for 48 hours prior to application and until "dry" and stable. Avoid extreme air movement over ceilings as it may cause cracking.

Surface Preparation: _____

All surfaces must be firm, clean, dry and free of foreign substances. Concrete surfaces must be aged at least 60 days prior to Ultra-Ceil application. Particular caution should be exercised to determine the presence of efflorescence, dirt, dust, grease, separating and/or bond breaking agents, or a latent layer of cement. After removal of any of the foregoing, any irregularities larger than 3 mm (1/8") in the concrete surface should be filled and smoothed with Hamilton Drywall Products Ultra-Fill. Metallic particles must be spot-primed with an alkyd flat paint prior to Ultra-Ceil application.

Mixing: _____

In a clean container and with clean tools mix mechanically with approximately 13.5 litres of clean water per 15kg bag. Slowly add powder to water and continue mixing until mixture is free of lumps. Re-mix after a few minutes adding more water as required. Mix no more material than can be used prior to material hardening and do not re-temper. Clean tools and mixing containers thoroughly with clean water prior to material hardening.

Application: _____

For interior use only. Apply with a trowel or knife - use in automatic tools only if approved by tool manufacturer. Do not apply thicker than 3 mm (1/8") in one coat. Because a lot of moisture is released during drying, appropriate ventilation and moisture escape from the building is absolutely necessary. Top angles should be taped flat onto ceiling or tape should be cut in the angle after dry to avoid structural movement from pulling tape down.

Coverage/Yield: _____

14-19 square meters (150-200 square feet) per 15 kg bag.
Approximate yield per 15 kg bag – 28 litres.

Decoration: _____

Finer textures may require two coats of Ultra-Ceil. To obtain a very smooth surface apply a top coat of any drywall compound. A coat of a quality texture primer is strongly recommended prior to texture application. Occasionally, due to high amounts of impurities in the substrate, discoloration may appear through the texture. If this occurs, apply a coat of a good quality Alkyd paint to seal the surface prior to additional decoration.

Storage/Shelf Life: _____

Rotate inventory regularly and store in a dry and low humidity environment.

Hamilton Drywall Products Canada
655 West Kent Avenue North, Unit 500
Vancouver, BC, V6P 6T7
(604) 515-0630 • hamiltondp.com

Hamilton Drywall Products USA
295 North Pekin Road
Woodland, WA 98674
(800) 871-4998 • hamiltonnw.com

Submittal Approvals

Job Name:

Contractor:

Date:

Hamilton Drywall Products Canada
655 West Kent Avenue North, Unit 500
Vancouver, BC, V6P 6T7
(604) 515-0630 • hamiltondp.com

Hamilton Drywall Products USA
295 North Pekin Road
Woodland, WA 98674
(800) 871-4998 • hamiltonnw.com